

## Flügger Floor Paint Epoxy - Chemical Resistance

October 2018

Assessment of the short-term impact of chemicals on a painted surfaces. This list is compiled on the basis of completed laboratory tests according to SIS 184161.

Explanation of classification:

- 4** Persistent
- 3** Resistant but discolored
- 2** Easier damage / deterioration of adhesion
- 1** Highly injured

Acetone (propanone)	1	Mineral Oil	4
Ammonia 10%	4	Lactic acid (2-hydroxypropan acid) 10%	3
Petrol 96 octane	4	Formic Acid 10%	1
Brake fluid Dot	4	Sodium hydroxide 10%	4
Diesel	4	Beetroot	3
Ethanol	2	Nitric acid 10%	3
Ethyl acetate	2	Silicone oil	4
Glycol (Propylene glycol)	4	Sulfuric acid 10%	3
Hydraulic oil	4	Hydrogen peroxide 10%	3
Isopropyl alcohol	3	Xylene	3
Lime	4	Acetic acid 10%	1
White Spirit (17-20% aromatic)	4	Acetic acid 1%	4